

# NOR|Strato

*Flex*

No.1 May 2020

Basis Werte / values	ISO	Einheit / unit		
Flächengewicht/ Grammage	536	g/m <sup>2</sup>	45	55
Feuchte/Moisture	287	%	7,5	7,5
Reißlänge (längs) / Breaking strength m.d.	1924	N	35	40
Reißlänge (quer) / Breaking strength c.d.	1924	N	10	13
Durchreißwiderstand längs / Tear index m.d	1974	Nm <sup>2</sup> /kg	4	4,5
Durchreißwiderstand quer / Tear index c.d.	1974	Nm <sup>2</sup> /kg	5	5,7
Bertsdruck / burst	2758	kPa	65	85
Specific volume / Specific volume	534	cm <sup>3</sup> /g	1,5	1,5
Rauigkeit Bendtsen / Roughness Bendtsen	8791-2	ml/min.	275	275
Weisse / Brightness	2470-2	D65/10° %	60	60
CIE L	5631-2	D65/10°	83	83
CIE a	5631-2	D65/10°	-0,3	-0,3
CIE b	5631-2	D65/10°	3.0	3.0
Opazität /Opacity	2471	%	96	98
Porosität / Porosity	Bendtsen	ml/min.	270	200

Bei den Daten handelt es sich um Durchschnittswerte, die entsprechend den üblichen Fertigungstoleranzen, nach oben und unten schwanken / data are production average values. There is an variability according to the industry common production deviations.

Verpackungspapier aus verstärkter Recyclingfaser für flexible Anwendungen , maximale Rollenbreite 2100mm / recycled fiber based packagingpaper for flexible packaging uses, maximum reel width 2100mm

## Zertifikate / certificates

für den Lebensmitteldirekontakt von Lebensmittel die keinen Migrationstest benötigen (trockene Lebensmittel) geeignet / intent to come in contact with foodstuffs for which migration tests are not requested (dry foods) EC no.1935/2004, direct. 80/590/EEC, direct. 89/109/EEC

